

URS 2060

HIGH TEAR & ABRASION RESISTANT POLYURETHANE SYSTEM

60 SHORE A

DESCRIPTION

URS 2060 is a medium viscosity polyester based urethane casting system with excellent dynamic and mechanical properties. **URS 2060** is designed for high abrasive applications where sliding and impinging types of abrasives are present as in, slurry pumps, sizing screens, chute liners, flotation components, etc.

FEATURES

Excellent Abrasion Resistance
Excellent Oil and Solvent Resistance
High Tear Strength
No MOCA or TDI
Hand or Machine Processing

LIQUID

PROPERTIES

POL 170B

ISO 160A

MIXED

Appearance	Amber Liquid	Dark Brown Liquid	Light Brown Liquid
Viscosity (cps)	3500-4500 (100F)	100-500 (77 F)	3400-4400 (100 F)
Density (lbs/gal)	8.70-8.90	10.0 – 10.2	8.90 – 9.10

PHYSICAL PROPERTIES

Hardness, Shore A	60
Modulus, psi, 100%	280
200%	400
300%	550
Tensile Strength, Ultimate, psi	2950
Elongation %	600
Split Tear PLI	240
Bayshore Rebound, %	45

URS 2060 Cont:

PROCESSING PARAMETERS

Melt and process polyol 170B at 100 to 150 degrees F.

Melt Isocyanate 160A if frozen at 100 degrees F., otherwise use at 70 to 85 degrees F.

Mold Temperature: 110 to 180 degrees F.

Mix Ratio: 100 parts Polyol 170B to 30.00 parts Isocyanate 160A by weight.

Degas mixture if possible or Pre-degas in dispensing equipment prior to casting.

Pot Life: (200g mass) (100 F) 12 to 15 minutes.

Demold: 1-2 hours or 30-45 minutes with maximum process and mold temperature. Catalyst may also be used to shorten demold time.

Post Cure: 16-24 hours @ 140 degrees F.

STORAGE

Systems should be stored unopened in air tight containers at 60-90 degrees F. Partially emptied. Containers should be swept free of atmospheric moisture with dry nitrogen before sealing.

HANDLING PRECAUTIONS

For complete and updated health and safety information, read the MATERIAL SAFETY DATA SHEETS. Do not handle or use until the MATERIAL SAFETY DATA SHEET has been read and understood.