

EPS 2811

EPOXY POTTING & ADHESIVE SYSTEM

DESCRIPTION

EPS 2811 is a lower viscosity version of EPS 2810 with the same excellent physical properties at a greatly reduced viscosity for void free castings. EPS 2811 applications include grouts, concrete coatings, floor mortar, etc.

FEATURES

Unfilled
Rigid 75 D
Excellent Electrical Properties
Low Viscosity
Good Hydrolytic Stability
Long Pot Life
Outstanding Adhesion

Liquid

Properties

	<u>Epoxy 260A</u>	<u>AMN 360B</u>	<u>Mixed</u>
Appearance	Amber Liquid	Lt. Brown Liquid	Lt. Brown Liquid
Viscosity (cps)	400-1,500 (77F)	500-1,500 (77F)	500-1,500 (77F)
Density (lbs/gal)	9.50-9.70	9.00-9.20	9.30-9.50

PHYSICAL PROPERTIES

Hardness, Shore D	75
Dielectric Constant (KHZ)	3.83
Dissipation Factor (KHZ)	0.14
Volume Resistivity ohm-cm	2.0 X 10 ¹⁵
Moisture Resistance 3 Weeks Immersion H ₂ O	
Weight Gain	0.5%
Impact Strength, Ft. Lbs/In	2.13
Compressive Strength (psi)	4300
Tensile Strength (psi)	3150
Elongation, %	30.00
HDT Deg F	104

EPS 2811 cont:

PROCESSING PARAMETERS

Process Epoxy resin 260A and Amine Hardener 360B between 55 and 150 Deg F.

Mold Temperature: 55 to 150 degrees F.

Mix Ratio: 100 parts Resin 260A to 50.0 parts Amine 360B by weight.

Degas mixture if possible.

Pot Life: (200g mass) (77 Deg F) 110 to 140 minutes.

Demold: 4-5 hours. Demold time maybe shortened by using higher mold and process temperatures.

Post Cure: 48 hours @ 77 degrees F.

STORAGE

Systems should be stored unopened in air tight containers at 60-90 degrees F.

HANDLING PRECAUTIONS

For complete and updated health and safety information, read the MATERIAL SAFETY DATA SHEETS. Do not handle or use until the MATERIAL SAFETY DATA SHEET has been read and understood.